

## Product information

# HYWAX 1800

printed on: 12.09.2022

Revision: 05.10.2021

Property	Specification	Unit	Method
Dropping point	78.0 .. 83.0	°C	ASTM D3954
Oil content	0.00 .. 2.00	%	ASTM D721
Needle penetration 25 °C	18 .. 22	1/10mm	ASTM D1321
Colour Saybolt	26 .. 30		ASTM D156
Kin. viscosity 100 °C	13.0 .. 17.0	mm <sup>2</sup> /s	ASTM D7042
BfR-conformance	conforms		BfR requirement XXV
Requirements USP/NF	conforms		USP/NF

Disclaimer: The information contained in this document is based on Hywax knowledge and experience at the time of its creation. We reserve the right to make any changes to this document or the products described therein, as a result of technological progress or developments. This information implies no liability or other legal responsibility on our part, including with regard to existing third-party patent rights. In particular, no guarantee or warranty of properties in the legal sense is implied. The customer is not exempted from the obligation to conduct careful inspection and testing of incoming products. All our business transactions are governed exclusively by our General Business Terms (<https://www.hywax.com/terms-conditions/>).

### Hywax GmbH

Gesellschaft mit beschränkter Haftung, Location Hamburg, Germany, Registration No. Hamburg HRB 73963

Managing Director: Giuseppe Ambroggio

VAT-No. DE 118 922 039 Tax No. 27/164/00096

[www.hywax.com](http://www.hywax.com) [info@hywax.com](mailto:info@hywax.com)