

Product information

Sasolwax 1800

printed on: 05.02.2021

Revision: 23.03.2020

Property	Specification	Unit	Method
Dropping point	78,0 .. 83,0	°C	ASTM D3954
Oil content	0,00 .. 2,00	%	ASTM D721
Needle penetration 25 °C	18 .. 22	1/10mm	ASTM D1321
Colour Saybolt	26 .. 30		ASTM D156
Kin. viscosity 100 °C	13,0 .. 17,0	mm ² /s	ASTM D7042
BfR-conformance	conforms		BfR requirement XXV
Requirements USP/ microcristal	conforms		USP

Sasol is a registered trademark of Sasol Ltd. Product trademarks displayed in this document are the property of the Sasol Group of companies, except where it is clear from the context that not. Users of this document are not permitted to use these trademarks without the prior written consent of their proprietor. All rights not expressly granted are reserved. Reference to trademarks used by other companies is neither a recommendation, nor should it give the impression that products of other companies cannot be used.

Disclaimer: The information contained in this document is based on Sasol's knowledge and experience at the time of its creation. We reserve the right to make any changes to this document or the products described therein, as a result of technological progress or developments. This information implies no liability or other legal responsibility on our part, including with regard to existing third-party patent rights. In particular, no guarantee or warranty of properties in the legal sense is implied. The customer is not exempted from the obligation to conduct careful inspection and testing of incoming products. All our business transactions are governed exclusively by our General Business Terms (<https://www.sasolgermany.de/de/agb/>).

Sasol Wax GmbH

Gesellschaft mit beschränkter Haftung, Location Hamburg, Germany, Registration No. Hamburg HRB 73963

Managing Director: Edwin Vorsteveld

VAT-No. DE 118 922 039 parent company Sasol Wax Int. GmbH Tax No. 27/164/00088

www.sasolwax.com wax@de.sasol.com